



U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

CMS - 2

Tests

Specifications

	Min.	Max.
Viscosity, Saybolt Furol @ 50° C (122° F).....	50.....	450
Storage Stability - 1 Day, %.....		1
Particle Charge.....	Positive	
Sieve Test, %.....		0.10
Distillation		
Oil Distillate, By volume of Emulsion, %.....		12
Residue, %.....	65	
Coating ability & Water resistance		
Coating, dry aggregate.....	Good	
Coating, after spraying.....	Fair	
Coating, wet aggregate.....	Fair	
Coating, after spraying.....	Fair	

Tests on Residue from Distillation

Penetration @ 25° C (77° F).....	100.....	250
Ductility @ 25° C (77° F).....	40	
Solubility in Trichlorethylene, %	97.5	

Meets or Exceeds: AASHTO M-140 and WDOT specifications