



U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

CRS - 2

Tests

Specifications

	Min.	Max.
Viscosity, Saybolt Furol @ 50° C (122° F).....	150.....	300
Storage Stability - 1 Day, %.....		1
Particle Charge.....	Positive	
Sieve Test, %.....		0.10
Distillation		
Oil Distillate, By volume of Emulsion, %.....	1.5.....	3.0
Residue, %.....	65	
Demulsibility test.....	40	

Tests on Residue from Distillation

Penetration @ 25° C (77° F).....	100.....	250
Ductility @ 25° C (77° F).....	40	
Solubility in Trichlorethylene, %	97.5	

Meets or Exceeds: AASHTO M-140 and WDOT specifications