



U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

CSS-1H

Tests

Specifications

	Min.	Max.
Viscosity, Saybolt Furol @ 25° C (77° F).....	20.....	100
Storage Stability - 1 Day, %.....		1
Particle Charge.....	Positive ¹	
Sieve Test, %.....		0.10
Cement Mixing, %.....		2.0
Distillation		
Asphaltic Residue, %.....	57	

Tests on Residue from Distillation

Penetration @ 25° C (77° F).....	40.....	90
Ductility @ 25° C (77° F).....	40	
Solubility in Trichloroethylene, %	97.5	

Note 1:

If the particle charge is inconclusive, material having a maximum pH value of 6.7 is acceptable.

Meets or Exceeds: AASHTO M-140 and WDOT specifications