



U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

CRS - 2P

Tests

Specifications

	Min.	Max.
Viscosity, Saybolt Furol @ 50° C (122° F)	150.....	400
Storage Stability - 1 Day, %		1
Particle Charge.....	Positive	
Sieve Test, %		0.30
Distillation (1)		
Oil Distillate, By volume of Emulsion, %		3.0
Residue, %	65	
Demulsibility test.....	40	

Tests on Residue from Distillation

Penetration @ 25° C (77° F)	100.....	250
Elastic Recovery, %	40	
Toughness/Tenacity Newton-meters,	50/25	

Conforms to WDOT specifications