



# U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

## CRS - 2P

### Tests

### Specifications

	<b>Min.</b>	<b>Max.</b>
Viscosity, Saybolt Furol @ 50° C (122° F).....	100.....	400
Storage Stability - 1 Day, %.....		1
Particle Charge.....	Positive	
Sieve Test, %.....		0.30
Distillation (1)		
Oil Distillate, By volume of Emulsion, %.....		3.0
Residue, %.....	65	
Demulsibility test.....	40	

### Tests on Residue from Distillation

Penetration @ 25° C (77° F).....	100.....	250
Torsional Recovery,% or.....	18	
Toughness/Tenacity Newton-meters, .....	5.6/2.82	

Meets or Exceeds: WDOT specifications