



# U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

## STE-1

### Tests

### Specifications

	<b>Min.</b>	<b>Max.</b>
Viscosity, Saybolt Furol @ 25° C (77° F).....		30
Storage Stability - 1 Day, %.....		1
Particle Charge.....	Positive	
Sieve Test, %.....		0.10
Distillation		
Oil Distillate, By volume of Emulsion, %.....		5
Residue %.....	45	
Demulsibility Test.....	25	

### Tests on Residue from Distillation

Penetration @ 25° C (77° F).....	100.....	200
Ductility @ 25° C (77° F).....	40	
Solubility in Trichlorethylene, % .....	97.5	

Meets or Exceeds: WDOT specifications