



# U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

## AC - 2.5

### Tests

### Specifications

	<b>Min.</b>	<b>Max.</b>
Viscosity @ 60° C (140° F), Pa s (Poise).....	20 (200).....	30 (300)
Viscosity, Kinematic @ 135° C (275° F), mm <sup>2</sup> / s		
Table 1.....	80	
Table 2.....	125	
Penetration @ 77° F (25° C ), dmm		
Table 1.....	200	
Table 2.....	220	
Flash Point, COC.....	163° C (325° F)	
Solubility in Trichloroethylene, %.....	99.0	

### Tests on RTFO Aged Residue

Viscosity @ 60° C (140° F), Pa s (Poise).....	100 (1000)
Ductility @ 25° C (77° F), cm.....	100

Meets or Exceeds:  
AASHTO M226-80 (86) Table 1  
AASHTO M226-80 (86) Table 2