



# U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

## **AR - 6000**

### Tests

### Specifications

	<b>Min.</b>	<b>Max.</b>
Flash Point, COC.....	232° C (450° F)	
Solubility in Trichloroethylene, %.....	99.0	

### Tests on RTFO Aged Residue

Viscosity, Absolute @ 60° C (140° F), Pa s (Poise).....	500 (5000).....	700 (7000)
Viscosity @ 135° C (275° F), mm <sup>2</sup> / sec (cSt) .....	350	
Penetration @ 25° C (77° F), dmm.....	25	
Percent of Original Penetration @ 25° C (77° F).....	50	
Ductility @ 25° C (77° F), cm.....	75	