



U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

PG 64 - 22

	Minimum	Maximum
Flash Point, COC, ° C.	230	
Viscosity @135 °C., Pa ·s		3.0
Dynamic Shear @ 64 °C., G*/sin ,kPa	1.00	
After RTFO		
Dynamic Shear @ 64 °C., G*/sin , kPa	2.20	
Mass Loss, %		1.00
After PAV @100 °C		
Dynamic Shear @ 25 °C., G*·sin , kPa		5000
Creep Stiffness @ -12 °C., S., MPa		300
Creep Stiffness @ -12 °C., M-value	0.300	